

# Technical Data Sheet

ATI 6230™



## ATI 6230™

### Nickel-Based Superalloy

(UNS N06230)

#### GENERAL PROPERTIES

ATI 6230™ alloy is a solid-solution strengthened, Ni-Cr-W-Mo alloy that combines excellent high-temperature strength, resistance to creep rupture, and resistance to corrosion at elevated temperatures. The precipitation of chromium-rich  $M_{23}C_6$  carbides enhances the high temperature creep strength of the alloy. ATI 6230™ alloy has good resistance to oxidizing environments up to 2100°F (1149°C) due to its high chromium content and its silicon, manganese, and lanthanum additions. It offers excellent long-term metallurgical stability even after thermal exposure at intermediate temperatures. Additionally, the thermal expansion characteristics are lower than many high-temperature alloys and provides this alloy with resistance to thermal fatigue. Due to high Ni content, this alloy has good resistance to carburizing and nitriding environments.

#### Limiting Composition

Element	Weight %
C	0.05 – 0.15
Mn	0.30 – 1.00
Si	0.25 – 0.75
P	0.25 – 0.75
S	0.015 max
Cr	20.00 – 24.00
Mo	1.00 – 3.00
W	13.00 – 15.00
Al	0.20 – 0.50
La	0.005 – 0.05
Co	5.00 max
Ti	0.10 max
B	0.015 max
Fe	3.00 max
Cu	0.50 max
Ni	Balance

Data are typical, are provided for informational purposes, and should not be construed as maximum or minimum values for specification or for final design, or for a particular use or application. The data may be revised anytime without notice. We make no representation or warranty as to its accuracy and assume no duty to update. Actual data on any particular product or material may vary from those shown herein. TM is trademark of and ® is registered trademark of ATI Properties, LLC or its affiliated companies. The starburst logo is a registered trademark of ATI Properties, LLC. © 2019 ATI. All rights reserved.

# Technical Data Sheet

ATI 6230™



## Specifications

ASTM B435, ASME SB 435, AMS 5878, UNS N06230, DIN 17744 W.-Nr. 2.4733 and NiCr22W14Mo

ATI 6230™ alloy is approved for ASME Vessel Code Section I and Section VIII Division 1 construction to 1650°F (899°C) in Section II, Part D for plate, sheet, and strip.

## Product Forms

**Coil** – Width: Up to 36" (914 mm); inquire within for 48" (1219 mm)

Thickness: 0.020" - 0.250" (0.508 mm – 6.35 mm)

**Plate** - Inquire within

## Mechanical and Physical Properties

### Annealed Properties (Sheet)

0.2% Yield Strength	50 ksi (345 MPa) min.	Hardness	≤ 25 HRC
Tensile Strength	115 ksi (793 MPa) min.	Density	0.324 lb/in <sup>3</sup> (8.97 g/cm <sup>3</sup> )
Elongation	40% min.	Electrical Resistivity	49.2 μohm-in (125 μohm·cm)

### Mean Thermal Expansion Coefficient

70-200°F	6.5	μin/in°F
70-400°F	6.9	μin/in°F
70-600°F	7.2	μin/in°F
70-800°F	7.4	μin/in°F
70-1000°F	7.6	μin/in°F
70-1200°F	8.0	μin/in°F
70-1400°F	8.3	μin/in°F
70-1600°F	8.6	μin/in°F
70-1800°F	8.9	μin/in°F

Data are typical, are provided for informational purposes, and should not be construed as maximum or minimum values for specification or for final design, or for a particular use or application. The data may be revised anytime without notice. We make no representation or warranty as to its accuracy and assume no duty to update. Actual data on any particular product or material may vary from those shown herein. TM is trademark of and ® is registered trademark of ATI Properties, LLC or its affiliated companies. The starburst logo is a registered trademark of ATI Properties, LLC. © 2019 ATI. All rights reserved.



# Technical Data Sheet

ATI 6230™



## Stress Rupture Requirement of AMS 578 Specification

Temperature	Stress	Minimum Life	Minimum Elongation
1700°F	9 ksi	36 hrs	10%