

SANDVIK 6LR62

TUBE AND PIPE, SEAMLESS

DATASHEET

Sandvik 6LR62 is a molybdenum-alloyed austenitic stainless steel.

STANDARDS

- ASTM: TP316, TP316H
- UNS: S31600, S31609
- EN Number: 1.4401
- EN Name: X5CrNiMo17-12-2
- W.Nr.: 1.4401
- AFNOR: Z6ZND17-12

CHEMICAL COMPOSITION (NOMINAL) %

Chemical composition (nominal) %

C	Si	Mn	P	S	Cr	Ni	Mo
0.05	0.6	1.5	≤0.040	≤0.015	17	11.5	2.1

MECHANICAL PROPERTIES

At 20°C (68°F)

Proof strength		Tensile strength		Elong.
Rp0.2a)		Rm		Ab)
MPa	ksi	MPa	ksi	%
≥205	≥30	515-790	75-115	≥45

1 MPa = 1 N/mm²

a) Rp0.2 and Rp1.0 correspond to 0.2% offset and 1.0% offset yield strength, respectively.

b) Based on $L_0 = 5.65 \sqrt{S_0}$ where L_0 is the original gauge length and S_0 the original cross-section area.

At high temperatures

Metric units

Temperature	Proof strength
	Rp0.2
°C	MPa
	min.
50	196
100	175

Metric units

Temperature	Proof strength
	Rp0.2
°C	MPa
	min.
150	158
200	145
250	135
300	127
350	120
400	115
450	112
500	110
550	108

Imperial units

Temperature	Proof strength
	Rp0.2
°F	ksi
	min.
200	26
400	21
600	18
800	16
1000	16

Creep strength

Temperature		Creep-rupture strength			
°C	°F	10 000h		100 000h	
		MPa approx.	ksi approx.	MPa approx.	ksi approx.
550	1020	255	37.0	177	25.7
575	1065	214	31.0	137	19.9
600	1110	172	24.9	108	15.7
625	1155	137	19.9	86	12.5
650	1200	108	15.7	64	9.3
675	1245	83	12.0	46	6.7
700	1290	64	9.3	33	4.8
725	1335	49	7.1	25	3.9
750	1380	37	5.4	18	2.6

WELDING

The weldability of Sandvik 6LR62 is good. Welding must be carried out without preheating and subsequent heat

treatment is normally not required. Suitable methods of fusion welding are manual metal-arc welding (MMA/SMAW) and gas-shielded arc welding, with the TIG/GTAW method as first choice.

For Sandvik 6LR62, heat input of <2.0 kJ/mm and interpass temperature of <150°C (300°F) are recommended.

Recommended filler metals
TIG/GTAW or MIG/GMAW welding

ISO 14343 S 19 12 3 H / AWS A5.9 ER316H

MMA/SMAW welding

ISO 3581 E 19 12 2 R / AWS A5.4 E316H-17

Disclaimer: Recommendations are for guidance only, and the suitability of a material for a specific application can be confirmed only when we know the actual service conditions. Continuous development may necessitate changes in technical data without notice. This datasheet is only valid for Sandvik materials.